



Matte Armor 2k Sealer



COVERAGE:

1 gallon (3.8 Liters) covers approximately:
- 1st application: 300-350 sq ft
- 2nd application: 350-400 sq ft

PACKAGING:

- Available in 1 gallon jugs.
Special quantities available upon request.

STORAGE:

- Keep in a cool, dry location out of direct sunlight.
- Protect pails and jugs from weather and other damage.
- Store at a temperature between 40°F (4°C) and 90°F (32°C).

SHELF LIFE:

- 14 months in original sealed container.

COLOR:

- K_{rrc} / Can Add Color

Visit our Youtube channel for How-to Videos and our Instagram for inspiration!



@ClassicCoatingSystems



@ClassicCoatingSystems

An Aliphatic-Polyurethane 2 Part Sealer and Color Enhancer

DESCRIPTION

Classic Matte Armor 2K Aliphatic-Polyurethane Sealer is a clear, 2-part component, voc < 1g/l 63% solids, waterborne, special blend sealer that is designed to be used over all of our stains, as well as polymer modified cementitious toppings, masonry, concrete and waterborne colorants. May be used for exterior & interior. Matte Armor 2k provides UV stability and will not yellow. CRU repels water, oil, chemicals, and acid. It is formulated primarily as a clear sealer for durable protection over concrete restoration projects and is low maintenance. It is typically applied with a 9"x1/2" nap roller with 1-hour pot life, provided that the surface is properly prepared. Matte Armor 2K is environmentally safe and cleans up with water. Also available in high gloss or in a satin finish. Color additives are also available in solid colors and metallic colors. Caution: Sealers may be slippery when wet. If desired, add Classic Gator Grip during the second application only. **New concrete must cure for 28 days before sealer is applied. Professional use only.**

ADVANTAGES

Excellent adhesion and durability
Nano technology with voc<1 and low odor

UV Stable and fast drying
Low cost, easy installation, & low maintenance

No fumes, non-hazmat and non-corrosive

No hot tire pick up after 5 days & heat resistant

FDA secondary grade

Longer than usual pot life of 1 hour

Excellent as a protective floor coating.
CRU repels water, oil, chemicals, and acid

LIMITATIONS

Application surface temperature should be between 55°F and 110°F

Never apply adhesives over stained or sealed surfaces. May cause damage.

Will reflect working cracks in substrate and do not allow to puddle

Must be installed over a clean and dry surface

Do not freeze. Keep container closed when not in use and out of sun

Must cure for 4 to 5 days before parking a vehicle on it.

TYPICAL USAGE

- Commercial, industrial, warehouse, retail stores, restaurant & office.
- Residential, driveways, pools, walkways & concrete decks.
- Restoration projects and architectural toppings.
- Concrete, bricks, flagstone, stone, epoxy, metal & pavers.



Matte Armor 2k Sealer

An Aliphatic-Polyurethane 2 Part Sealer and Color Enhancer

SURFACE PREPARATION

✓ READ SDS BEFORE HANDLING & APPLICATION

- ✓ Highly recommended to test a small inconspicuous area first.
- ✓ TURN OFF SPRINKLERS FOR TWO DAYS PRIOR TO AND AFTER.
- ✓ Always protect neighboring surfaces including wood, carpet, metal, landscaping and other non-masonry surfaces.
- ✓ Clean concrete with Classic Super Eco-Etch before staining.
- ✓ Before you start staining wear rubber gloves & safety glasses
- ✓ New concrete must cure for 28 days before stain is applied.
- ✓ Note: For older concrete, water based stains work the best.

Surface preparation is one of the most important steps of the staining process. The concrete must be free of debris, dirt, and oils. Start by cleaning the surface with Classic Super Eco-Etch on broom finished and smooth finished concrete. Clean twice with Classic Super Eco-Etch and pressure wash the concrete with fresh water at 2,800 psi. Rinse the surface with fresh water to remove any softened concrete created by the etching and pressure washing process. For sandblasted concrete, clean one time with Classic Super Eco-Etch and pressure wash the concrete with fresh water at 2,800 psi. Rinse the surface with fresh water. For Stamp concrete and smooth concrete surfaces the process is the same.

Often, surfaces inside an existing house will have dry wall mud, paint, wood stains, tile adhesives and carpet adhesives, grease, pet stains, etc on the concrete. These spots will show through if not removed as these get into the pores of the concrete and block the staining process. There are several products available at a local hardware store such as adhesive removers and lacquer thinners that can be used to clear these products from concrete. Cleaning one of these floors to a stainable level is a considerable amount of work but not impossible. If you desire a more even finish consider one of our overlay resurfacing products like Classic Stamp Overlay (white). White always shows a better color. For indoor use, apply Classic Micro Topping (white), especially on a floor that has had glued tile or glued carpet.

When staining an area, cover the surrounding areas thoroughly with drop cloths and clear plastic sheeting including plants and furniture so that nothing is accidentally stained, stains can be difficult if not impossible to remove. The appearance of the finished product is very much influenced by the manner in which the stain is applied. The stain can be sprayed, mopped, brushed, rubbed, but the best way is using a plastic sprayer and a push broom, etc. We suggest to spray on method using an all plastic pump sprayer (no metal parts) and a push broom brush in circular strokes. Once the surface is completely dry you can finally move onto sealing it.

HOW TO MIX – PER GALLON

Mix Part A very well for 5 – 6 minutes. Once done, add Part B to Part A and mix with a slow speed drill that has a mixing paddle attachment. Move the drill up and down the container to mix it together well. A & B should be mixed together for 4 minutes. Be sure to carefully scrape the sides and the bottom of the container while mixing. Please note: Large batches of sealer will cure much faster in hot weather than in cold weather. Keep the mixture close and in a cool area. Mix well every few minutes before using. May lose a small amount of gloss and solids by adding the water. If water is added, use a 2 gallon pail to mix it with Part A and Part B.

***Pot life once Part A & Part B are mixed together is up to 35-40 minutes.**

***We highly recommend you prime the surface using CW200 for interior or PT30 for interior & exterior before applying the sealer.**

APPLICATION

Prime the surface with TP30 by following label instructions and allow to cure a minimum of 3 hours (75°F) prior to proceeding with the next coat sealer. We do not recommend applying the sealer on surfaces over 90 F. Test a small area first. Use a 9" or 18" NAP 3/8 or 1/2" Roller to spread evenly. Do not allow the sealer to puddle. Back roll if necessary. Begin by cutting in the edges and trim with the brush. The center may be done like you would normally paint a surface while making sure you overlap and back roll each section carefully. Remember to mix the sealer very well before every application.

Second Application: Apply a second application after 8 hours at around 75 F. Allow light foot traffic after 24 hours. Allow heavy traffic after 72 hours at 75 F with 50% humidity. Pot life is 35 minutes. In hot working conditions, place container of sealer in a bucket of ice to extend your working time.

MAINTENANCE

Maintaining a Classic Sealed Finished Surface and adherence to a strict maintenance schedule will help maximize its performance, appearance and slip resistance and will reduce the absorption of spilled liquids. Sealing the floor permits the floor to retain its aesthetic quality. Prompt removal of liquids is critical in minimizing slip hazards as well as staining.

Daily Maintenance and Cleaning: Once fully cured, routinely sweep, dry mop and wash with neutral pH cleaners and water. Spot clean and dry areas of concentrated traffic as needed. Do not use abrasive brushes or pads as part of a daily maintenance program. The use of mechanical cleaning devices, such as auto scrubbers and swing buffers with non-abrasive 3M Sky Blue maintenance pads, may be employed as needed when a sacrificial wax layer is applied. All mechanical cleaning devices must have the ability to remove all residual ponding water and cleaning agents. Do not use cleaners that are acidic or contain citrus (d limonene) or butyl compounds. The application of highly acidic cleaners may etch or stain the surface and reduce the floor's ability to resist water penetration. Prior to commencement of any maintenance, on-site test areas of the selected cleaner should be done to ensure compatibility.

Reapplication: For applications where a sacrificial wax layer has not been applied / maintained, it will be necessary to evaluate the sealer periodically to assess its ability to repel staining agents. Reapply as necessary and in accordance with this technical data sheet for optimum performance.

HANDLING PRECAUTIONS:

Use only with adequate ventilation. An appropriate cartridge type respirator must be used during application in confined areas. Avoid contact with skin. Protective gloves, eyewear and clothing are recommended.

PROP 65 WARNING:

Classic Coatings, as a blender of processed material in the State of California, is required by Proposition 65 to warn that one or more of the components contained in the product contain chemicals known to the State of California to cause cancer, birth defects or other reproductive harm. The State of California (Proposition 65) requires this warning in the absence of definitive testing to prove that the defined risks do not exist. We believe this product complies with all other applicable state and federal laws and regulations governing manufacturing, distribution and intended use. User is solely responsible for the legal disposal of this container and/or its contents.

WARRANTY:

Classic Coatings Systems products are warranted for one year after date of purchase. Please refer to the Limited Material warranty for additional clarification. NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY. We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE

THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET & FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.

Technical assistance and info. is available by calling: (951) 279-2600
www.ClassicCoatingsSystems.com